

国家葡萄酒质量监督检验中心检验报告
The Report by National Centre of Wine Quality Supervision & Inspection

No.: (2006) 2110507

共 2 页 第 1 页 Total 2 pages, page 1

Product name	Recoverable plastic synthetical wine cork	Registered trademark	—
Specification and model	TBL44—Φ22	Type of inspection	Entrustment
Inspected unit	Top Cork (Ruian) Co., Ltd	Sample grade	Qualified product
Manufacturing unit	Top Cork (Ruian) Co., Ltd	Person of sending sample	Chen Qinbin
Sampling location	—	Date of sending sample	2006-07-25 July 25 in 2006
Sample quantity	30 pieces	Date of inspection	2006-07-30 July 31 in 2006
Sample base number	—	Sample serial number	211060516
Characteristic and appearance of sample	Perfect	Original serial number and date of production	—
Environment of inspection	Temperature: —℃ Relative humidity : —% Air pressure: —MPa ■ According to standard request		
According as inspection	Q/ YTB001-2006 (draft)		
Conclusion of inspection	Inspected items conform to standard provision. Date of sign and issue: August 1 in 2006 (seal) Exclusive use seal of inspection of National Centre of Wine Quality Supervision & Inspection		
备注 Remarks	/		

批准: 张燕

Approval: Zhangyan

审核: 许雪柏

Verification: Xu Xuebai

主检: 谢淑兰

Main inspector: Xie Shulan

国家葡萄酒质量监督检验中心检验报告附页

Attached page to Report by National Centre of Wine Quality Supervision & Inspection

No.: (2006) 2110507

2006年8月1日 August 1 in 2006

共 2 页 第 2 页 Total 2 pages, page 2

Ordinal number	Name of Item inspected	Technical standard request	Unit of measurement	Result of inspection	Single item judgment
1	Residue on evaporation	≤30	mg/L	6	qualified
	4% acetic acid 60°C, 2h 65% ethanol, 20°C, 2h	≤30	mg/L	11	qualified
2	Consumption of potassium permanganate 60°C, 2h	≤10	mg/L	4	qualified
3	Heavy metal (metering in pb) 4% acetic acid, 60°C, 2h	≤1	mg/L	<1	qualified
4	Decolorization test	negative	/	negative	qualified
	Ethanol	negative	/	negative	qualified
	Edible oil or transparent fat and oil	negative	/	negative	qualified
	Soak solution	negative	/	negative	qualified

以下空白 Thereinafter blank

烟台市产品质量监督检验所检验报告
The Report by Yantai Institute for Quality Supervision & Inspection of Product

No.: (2006) 2050409

共 2 页 第 1 页 Total 2 pages, page 1

Product name	Recoverable plastic synthetical wine cork	Registered trademark	—
Specification and model	TBL44—Φ22	Type of inspection	Entrustment
Inspected unit	Top Cork (Ruian) Co., Ltd	Sample grade	Qualified product
Manufacturing unit	Top Cork (Ruian) Co., Ltd	Person of sending sample	Chen Qinbin
Sampling location	—	Date of sending sample	2006-07-25 July 25 in 2006
Sample quantity	30 pieces	Date of inspection	2006-07-26 July 26 in 2006
Sample base number	—	Sample serial number	205060427
Characteristic and appearance of sample	Perfect	Original serial number and date of production	—
Environment of inspection	Temperature: —℃ Relative humidity : —% Air pressure: —MPa ■ According to standard request		
Accordinging as inspection	Q/ YTB001-2006 (draft)		
Conclusion of inspection	Inspected items conform to standard (draft) provision. Date of sign and issue: July 31 in 2006 (seal) Exclusive use seal of inspection of Yantai Institute for Quality Supervision & Inspection of Product		
备注 Remarks	/		

批准: 李红
Approval: Lihong

审核: 杨国明
Verification: Yang Guoming

主检: 刘建君
Main inspector: Liu Jianjun

烟台市产品质量监督检验所检验报告附页

Attached page to Report by Yantai Institute for Quality Supervision & Inspection of Product

No.: (2006) 2050409

2006年7月31日 July 31 in 2006

共 2 页 第 2 页 Total 2 pages, page 2

Ordinal number	Name of Item inspected	Technical standard request	Unit of measurement	Result of inspection	Single item judgment
1	Dimensions				
1.1	Length	44±1	mm	44	Qualified
1.2	Diameter	22±0.5	mm	21.5(+)-21.9	Qualified
1.3	Ellipticity	≤0.4	mm	0.1~0.2	Qualified
2	Appearance quality	4.1 article in the Q/ YTB001-2006 standard (draft)	/	measure up to standard provision	Qualified
3	Degree of hardness (Shore A)	60-85	Degree	73-80	Qualified
4	Extraction force	330-520	KPa	338~359	Qualified
5	Forced down Force	190-400	N	216~277	Qualified
6	Rebound degree	≥95	%	97	Qualified
7	Sealing property	No leakage in 24 hours	/	measure up to standard provision	Qualified

Thereinafter blank